

SSAB Domex Tube 460MH

General Product Description

SSAB Domex Tube 460MH is high strength structural hollow section.

It meets or exceeds the requirements of EN 10219 and is available in circular, rectangular, square and special shapes. Customized shapes and other tailoring options are available upon request. It is typically used in advanced engineering and construction where weight reduction, lower costs and safety are important.

SSAB Domex Tube 460MH is manufactured by cold forming and high frequency welding from clean, high quality environmentally friendly steel by modern and efficient tube lines. SSAB Domex Tube 460MH is high strength structural hollow section. It meets or exceeds the requirements of EN 10219 and is available in circular, rectangular, square and special shapes. Customized shapes and other tailoring options are available upon request. It is typically used in advanced engineering and construction where weight reduction, lower costs and safety are important. SSAB Domex Tube 460MH is manufactured by cold forming and high frequency welding from clean, high quality environmentally friendly steel by modern and efficient tube lines.

Dimension Range

SSAB Domex Tube 460 MH is available at circular, square and rectangular shapes.

Circular	42.4 - 323.9 mm
Square	40x40 - 300x300 mm
Rectangular	50x30 - 400x200 mm
Wall thickness	2.0 - 12.50 mm
Mill length	6000 - 12 000/18 000 mm

Other shapes and sizes are available upon request.

Dimensions

Circular

Diameter	2.0mm (kg/m)	3.0mm (kg/m)	4.0mm (kg/m)	5.0mm (kg/m)	6.0mm (kg/m)	8.0mm (kg/m)	10.0mm (kg/m)	12.5mm (kg/m)
42.4 mm	1.99	2.19						
48.3 mm	2.28	3.35	4.37					
60.3 mm	2.88	4.24	5.55	6.82				
76.1 mm		5.41	7.11					
88.9 mm		6.36	8.38	10.4				
101.6 mm		7.29	9.63	11.9				
108 mm		7.77	10.3	12.7				
114.3 mm		8.23	10.9	13.5				
127 mm		9.17	12.1	15.0				
133 mm		9.62	12.7	15.8				
139.7 mm		10.1	13.4	16.6	19.8	26.0	32.0	
152.4 mm			14.6	18.2				
159 mm			15.3	19.0	22.6	x	x	
168.3 mm			16.2	20.1	24.0	31.6	39.0	
193.7 mm				23.3	27.8	36.6	45.3	
219.1 mm				26.4	31.5	41.7	51.6	
273 mm				33.1	39.5	52.3	64.9	80.3
323.9 mm					47.0	62.3	77.4	96.0

Square

Height x Width	2.0mm (kg/m)	3.0mm (kg/m)	4.0mm (kg/m)	5.0mm (kg/m)	6.0mm (kg/m)	8.0mm (kg/m)	10.0mm (kg/m)	12.5mm (kg/m)
40 x 40 mm	2.31	3.30	4.20					
50 x 50 mm	2.93	4.25	5.45					
60 x 60 mm	3.56	5.19	6.71	8.13				
70 x 70 mm		6.13	7.97	9.70				
80 x 80 mm		7.07	9.22	11.3	13.2			
90 x 90 mm		8.01	10.5	12.8	15.1			
100 x 100 mm		8.96	11.7	14.4	x	21.4		
110 x 110 mm		9.90	13.0					
120 x 120 mm		10.8	14.3	17.6	20.8	26.4		
140 x 140 mm			16.8	20.7	24.5	31.4	38.1	
150 x 150 mm			18.0	22.3	24.5	31.4	41.3	
160 x 160 mm				23.8	28.3	36.5	44.4	52.6
180 x 180 mm				27.0	32.1	41.5	50.7	60.5
200 x 200 mm				30.1	35.8	46.5	57.0	68.3
250 x 250 mm					45.2	59.1	72.7	88.0
300 x 300 mm					54.7	71.6	88.4	108

Rectangular

Height x Width	2.0mm (kg/m)	3.0mm (kg/m)	4.0mm (kg/m)	5.0mm (kg/m)	6.0mm (kg/m)	8.0mm (kg/m)	10.0mm (kg/m)	12.5mm (kg/m)
50 x 30 mm	2.31	3.30	4.20					
60 x 40 mm	2.93	4.25	5.45	6.56				
70 x 50 mm	3.56	5.19	6.71	8.13				
80 x 40 mm	3.56	5.19	6.71	8.13				
80 x 60 mm		6.13	7.97	9.70				
90 x 50 mm		6.13	7.97	9.70				
100 x 50 mm		6.60	8.59	10.5				
100 x 60 mm		7.07	9.22	11.3				
100 x 80 mm		8.01	10.5	12.8				
120 x 50 mm		7.54	9.85	12.1				
120 x 60 mm		8.01	10.5	12.8				
120 x 80 mm		8.96	11.7	14.4				
120 x 100 mm		9.90	13.0	16.0				
140 x 80 mm		9.90	13.0	16.0				
150 x 100 mm		11.3	14.9	18.3	21.7	27.7		
160 x 80 mm			14.3	17.6	20.8	26.4		
160 x 90 mm			14.9	18.3	21.7	27.7		
180 x 100 mm				20.7	24.5	31.4	38.1	
200 x 100 mm				22.3	26.4	34.0	41.3	
200 x 120 mm				23.8	28.3	36.5	44.4	52.6
250 x 100 mm				26.18	31.11	40.23	49.11	x
250 x 150 mm				30.1	35.8	46.5	57.0	68.3
300 x 200 mm					45.2	59.1	72.7	88.0
400 x 200 mm					54.7	71.6	88.4	108

Mechanical Properties

Yield Strength Rp0.2 (min MPa)	Tensile Strength Rm (MPa)	Elongation A ₅ ²⁾ (min %)	Charpy-V -40°C 10x10 mm test specimen ¹⁾ (min J)
460	530 - 720	17	27

Mechanical properties meet or **exceed** the requirements of EN 10219.

The mechanical properties for rectangular hollow sections are tested by SSAB on the longer side of the cross section.

¹⁾ Impact testing according to EN ISO 148-1 is performed on thicknesses ≥ 6 mm. The specified minimum value corresponds to a full-size specimen.

²⁾ The hollow sections with $D/T < 15$ (round) or $(B + H)/2T < 12,5$ (rectangular and square), the minimum value of elongation is reduced by 2.

Chemical Composition (ladle analysis)

C (max %)	Si (max %)	Mn (max %)	P (max %)	S (max %)	Al _{tot} (min %)	Nb (max %)	V (max %)	Ti (max %)
0.16	0.25	1.70	0.020	0.012	0.020	0.090	0.120	0.060

Chemical composition meets or **exceeds** the requirements of EN 10219.

The steel is aluminium-killed.

Carbon equivalent

CEV (max %)	0.40
----------------	------

CEV value **exceeds** the requirements of EN 10219.

$CEV = C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15$

Tolerances

Characteristic	Circular hollow sections Tolerances meet or exceed the requirements of EN 10219
Outside diameter (D) ¹⁾	$\pm 1\%$, however a minimum of ± 0.5 mm and a maximum of ± 10 mm
Out-of-roundness	2%, when $D/T \leq 100$
Thickness (T)	When $D \leq 323.9$ mm: $-5\%/+10\%$, with a minimum of ± 0.2 mm and maximum ± 0.5 mm When $355.6 \leq D \leq 406.4$ mm ³⁾ : $\pm 10\%$, when $T \leq 5$ mm / ± 0.5 mm, when $T > 5$ mm When $D > 406.4$ mm ³⁾ : $\pm 10\%$, with a maximum of ± 2 mm
Straightness	0.20% of total length and 3 mm over any 1 m length
Mass per unit length	Individual tube: $\pm 6\%$
Mill length	0/+50 mm, $6000 \leq L \leq 12000 - 18000$ mm (standard lengths 6000 & 12000 mm)
Exact length	Agreed at the time of enquiry and order

¹⁾ All external dimensions are measured with a minimum distance from the end of the section. The distance must be a minimum of 100 mm.

Characteristic	Square hollow sections Tolerances meet or exceed the requirements of EN 10219
Outside dimensions (B, H) ¹⁾	When B, H < 100 mm ± 1 % minimum ± 0.5 mm When 100 mm \leq B, H \leq 200 mm: ± 0.8 % When B, H > 200 mm: ± 0.6 %
Thickness (T)	-5% / +10 %, with a minimum of ± 0.2 mm and maximum ± 0.5 mm
External corner profile	When $T \leq 6$ mm: $1.6 \times T - 2.4 \times T$ When $6 \text{ mm} < T \leq 10$ mm: $2.0 \times T - 3.0 \times T$ When $T > 10$ mm: $2.4 \times T - 3.6 \times T$
Squareness of side	$90^\circ \pm 1^\circ$
Concavity/convexity	0.8%, with a minimum of 0.5 mm
Twist	2 mm + 0.5 mm/m
Straightness	0.15% of total length and 3 mm over any 1 m length
Mass per unit length	Individual tube: ± 6 %
Mill length	0/+50 mm, $6000 \leq L \leq 12000 - 18000$ mm (standard lengths 6000 & 12000 mm)
Exact length	Agreed at the time of enquiry and order

¹⁾ All external dimensions are measured with a minimum distance from the end of the section. The distance must be a minimum of 100 mm.

Characteristic	Rectangular hollow sections Tolerances meet or exceed the requirements of EN 10219
Outside dimensions (B, H) ¹⁾	When B, H < 100 mm ± 1 % minimum ± 0.5 mm When 100 mm \leq B, H \leq 200 mm: ± 0.8 % When B, H > 200 mm: ± 0.6 %
Thickness (T)	-5% / +10 %, with a minimum of ± 0.2 mm and maximum ± 0.5 mm
External corner profile	When $T \leq 6$ mm: $1.6 \times T - 2.4 \times T$ When $6 \text{ mm} < T \leq 10$ mm: $2.0 \times T - 3.0 \times T$ When $T > 10$ mm: $2.4 \times T - 3.6 \times T$
Squareness of side	$90^\circ \pm 1^\circ$
Concavity/convexity	0.8%, with a minimum of 0.5 mm
Twist	2 mm + 0.5 mm/m
Straightness	0.15% of total length and 3 mm over any 1 m length
Mass per unit length	Individual tube: ± 6 %
Mill length	0/+50 mm, $6000 \leq L \leq 12000 - 18000$ mm (standard lengths 6000 & 12000 mm)
Exact length	Agreed at the time of enquiry and order

¹⁾ All external dimensions are measured with a minimum distance from the end of the section. The distance must be a minimum of 100 mm.

Contact Information

www.ssab.com/contact